



TWO PACK MIXING RATIOS CALCULATED BY WEIGHT


www.smlpaints.co.uk

ALL WEIGHTS ARE IN GRAMMES

Tel: 01285 862132

	To mix 0.5 litre by weight Comp A + Comp B = Total			To mix 1.0 litre by weight Comp A + Comp B = Total			To mix 1.5 litre by weight Comp A + Comp B = Total			To mix 2.0 litre by weight Comp A + Comp B = Total			To mix 2.5 litre by weight Comp A + Comp B = Total		
Hardtop AS	504	104	608	1008	208	1216	1512	312	1824	2016	416	2432	2520	520	3040
AS certain colours - see note 3 below *	438	104	542	876	208	1084	1314	312	1626	1752	416	2168	2190	520	2710
Hardtop AS Clear	371	130	501	742	260	1002	1114	390	1504	1485	520	2005	1856	650	2506
Hardtop AX	570	106	676	1140	212	1352	1710	318	2028	2280	424	2704	2850	530	3380
Hardtop CA	606	51	657	1212	102	1315	1818	154	1972	2425	205	2629	3031	256	3287
Hardtop Flexi	508	108	616	1016	216	1232	1524	324	1848	2032	432	2464	2540	540	3080
Hardtop HB	480	104	584	960	208	1168	1440	312	1752	1920	416	2336	2400	520	2920
Hardtop Optima	600	110	710	1200	220	1420	1800	330	2130	2400	440	2840	3000	550	3550
Hardtop XP	586	51	638	1173	103	1275	1759	154	1913	2345	205	2551	2932	257	3189
XP certain colours - see note 3 below *	525	51	576	1050	103	1153	1575	154	1729	2100	205	2305	1625	257	1882
Penguard Topcoat	452	95	547	904	190	1094	1356	285	1641	1808	380	2188	2260	475	2735
Jotafloor Topcoat	452	95	547	904	190	1094	1356	285	1641	1808	380	2188	2260	475	2735
Barrier	1144	113	1256	2287	225	2512	3431	338	3769	4575	450	5025	5719	563	6281
Barrier 90	1371	66	1438	2743	133	2876	4114	199	4314	5486	266	5751	6857	332	7189
Jotafloor Sealer	392	97	489	784	194	978	1176	291	1467	1568	388	1956	1960	485	2445
Jotafloor Solvent Free Primer	373	167	540	747	333	1080	1120	500	1620	1493	667	2160	1867	833	2700
Jotamastic 80 Std. Comp B	700	64	764	1400	128	1528	2100	191	2291	2800	255	3055	3500	319	3819
Jotamastic 80 W/G Comp B	640	102	742	1280	204	1484	1920	306	2226	2560	408	2968	3200	510	3710
Jotamastic 87 Std. Comp B	664	74	738	1329	147	1476	1993	221	2214	2657	294	2951	3321	368	3689
Jotamastic 87 AL. Std. Comp B	635	79	714	1269	158	1428	1904	238	2142	2538	317	2855	3173	396	3569
Jotamastic 87 W/G Comp B	620	102	722	1240	204	1444	1860	306	2166	2480	408	2888	3100	510	3610
Jotamastic 87 AL. W/G Comp B	590	109	699	1181	217	1398	1771	326	2097	2362	434	2796	2952	543	3495
Jotamastic 90	611	111	722	1221	222	1443	1832	333	2165	2442	444	2887	3053	556	3608
Jotamastic Smartpack	350	343	693	700	685	1385	1050	1028	2078	1400	1370	2770	1750	1713	3463
Jotacote Universal	548	120	668	1095	240	1335	1643	360	2003	2190	480	2670	2738	600	3338
Marathon 500	693	85	778	1386	170	1556	2079	255	2334	2772	340	3112	3465	425	3890
Muki EPS	555	13	567	1109	25	1135	1664	38	1702	2218	51	2269	2773	64	2836
Penguard Clear Sealer	392	95	487	784	190	974	1176	285	1461	1568	380	1948	1960	475	2435
Penguard Express ZP	668	97	765	1336	194	1530	2004	291	2295	2672	388	3060	3340	485	3825
Penguard HB	528	95	623	1056	190	1246	1584	285	1869	2112	380	2492	2640	475	3115
Penguard Primer	552	95	647	1104	190	1294	1656	285	1941	2208	380	2588	2760	475	3235
Penguard Low Temp Additive	in addition to Comp B		10	in addition to Comp B		20	in addition to Comp B		29	in addition to Comp B		39	in addition to Comp B		49

NOTES:

- You will require weighing scales that can measure to an accuracy of at least 5 grammes. **SUITABLE SCALES ARE ON OUR WEBSITE, LISTED UNDER "ACCESSORIES"**
- Put container on scales. Set scales to zero. Add Comp A to required weight. Add Comp B to make up to total weight. Mix thoroughly.
- * Jotun colours: 135,258,436,439,484,903
 * BS381c colours: 218,309,355,356,363,557,568
 * BS4800 colours: 06d43,06e56,08c37,08e51,10c53,10d43,10d45,12d43,12d45,12e51,12e53
 * RAL colours: 1003,1004,1005,1006,1007,1012,1016,1018,1021,1023,1027,1028,1032,1033,2000,2001,2002,2003,2004,2008,2009,2010,2011
- This sheet should be viewed as a guide only. It is based on the average specific gravities of the paints as stated in the Jotun Safety sheet. Actual SG will vary according to colour.